



TEST REPORT

No.: SDFTS25007364R03_EN

Date: Dec 16, 2025

Page 1 of 19

FOSHAN ZCAMP INTELLIGENT EQUIPMENT CO., LTD.

NO.3, ZHENZHU ROAD, YANG'E, LUNJIAO, SHUNDE, FOSHAN, GUANGDONG, CHINA

Sample Description : FLOOR OF PREFABRICATED HOUSES

The above sample(s) data and information was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Sample Receiving Date : Nov 25, 2025

Testing Period : Nov 25, 2025 to Dec 16, 2025

Test Required : EN 1364-2:2018 Fire resistance tests for non-loadbearing elements - Part 2:
Ceilings

Test result(s) : See attached sheet

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch

Ada

Ada Liu
Approved signatory

Scan to see the report



SDFTS25007364R03
Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

CONTENTS

1. INTRODUCTION	3
2. SUMMARY	3
3. SPECIMEN CONSTRUCTION AND INSTALLATION	3
4. TEST PROCEDURE	4
5. TEST DATA AND OBSERVATION	5
6. PERFORMANCE CRITERIA.....	13
7. CONCLUSION.....	14
8. CLASSIFICATION.....	14
9. LIMITATION	15
APPENDIX 1 - DRAWINGS	16
APPENDIX 2 - PHOTOS	17



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CS Standards Technical Service Co., Ltd.
Shunde Branch Inspection & Testing Services

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

1. INTRODUCTION

The test was conducted in accordance with EN 1363-1:2020, "Fire resistance tests - Part 1: General requirements" and EN 1364-2:2018, "Fire resistance tests for non-loadbearing elements – Part 2: Ceilings", to determine 30 minutes fire resistance performance of FLOOR OF PREFABRICATED HOUSES.

The FLOOR OF PREFABRICATED HOUSES was exposed to elevated temperatures as dictated by the time-temperature curve given in EN 1363-1:2020 for a period of 30 minutes. The sample was asymmetrical and was tested on the white surface towards the heating conditions of the test.

The test was conducted on Nov.26, 2025.

2. SUMMARY

The FLOOR OF PREFABRICATED HOUSE specimen satisfied the performance requirements for the following periods:

PERFORMANCE CRITERIA	RESULTS
Integrity	Sustained flaming 30 min
	Cotton pad test 30 min
	Gap gauge test 30 min
Insulation	30 min

The test was discontinued after a period of 30 minutes at the request of the sponsor.

3. SPECIMEN CONSTRUCTION AND INSTALLATION

The specimen for this fire resistance test was FLOOR OF PREFABRICATED HOUSES. The overall dimensions of the specimen was 4500 mm long by 3000 mm wide by 233 mm thick.

The tested sample was supported on the horizontal furnace with an opening of the 2800 mm by 4200 mm. The all around of the furnace wall was covered by ceramic fibre cotton. The tested sample was asymmetrical.

Detailed drawings and structural composition of the specimen are shown in Appendix 1 and were provided by the sponsor. The sample was sent to the laboratory by the sponsor.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

4. TEST PROCEDURE

The sample was tested under a non-loadbearing construction in accordance with EN 1364-2:2018, "Fire resistance tests for non-loadbearing elements – Part 2: Ceilings".

4.1 Furnace Temperature Control

The sample was tested in the horizontal test furnace of opening size 4200 mm × 4000 mm. Twelve furnace thermocouples, which were distributed uniformly in the furnace and were kept at 100±50 mm away from the exposed face of the test assembly, were provided to monitor the mean temperature of the furnace.

The average temperature in the furnace shall be raised and controlled according to the temperature/time requirements specified in Clause 5.1 of EN 1363-1:2020.

4.2 Furnace Pressure Control

The furnace pressure was monitored and controlled. The nominal pressure on the underside of the test specimen was set to be 18 Pa. The pressure condition was established 100 mm below the underside of the separating element. Five minutes after the commencement of the test the furnace pressure shall be ± 5 Pa of the nominal pressure specified for the particular element under test; from 10 min onwards it shall be ± 3 Pa of the nominal pressure specified for the particular element under test.

4.3 Integrity Monitoring

Cotton pads and gap gauges were available to evaluate the impermeability of specimen to hot gases. The occurrence of sustained flaming more than 10 s on the unexposed face was also checked to determine compliance with the integrity criterion.

4.4 Insulation Monitoring

The temperature on the unexposed surface of the specimen was measured by 9 measuring thermocouples. All above thermocouples were used to measure the temperature rise of individual points, and 1#~5# were also used to calculate the average temperature rise of the specimen.

When applicable, roving thermocouples can also be used to measure maximum temperature rise on the unexposed surface.

4.5 Deflection Measurement

After the test began, the deflection of the sample was measured by the wire displacement sensor. The sensor recorded a reading once per minute, and the measurement point was located at the center of the unexposed side of the sample under test.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com


5. TEST DATA AND OBSERVATION

5.1 Condition

The ambient air temperature in the vicinity of the test construction was 22.3 °C at the start of the test with variation of -0.8 °C during the test.

5.2 Furnace Temperature Record

The actual furnace temperature/time and standard furnace temperature/time curves are shown in below figure.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com



TEST REPORT

No.: SDFTS25007364R03_EN

Date: Dec 16, 2025

Page 6 of 19

The actual average temperatures within the furnace are recorded on the table below:

Time (min)	Standard Furnace Temperature (°C)	Actual Furnace Average Temperature (°C)	Deviation
0	20	28	-
1	349	202	-37.8%
2	445	384	-29.9%
3	502	501	-19.4%
4	544	543	-13.0%
5	576	574	-9.7%
6	603	598	-7.7%
7	626	618	-6.5%
8	645	632	-5.8%
9	663	650	-5.2%
10	678	661	-4.8%
11	693	682	-4.5%
12	705	696	-4.2%
13	717	705	-3.9%
14	728	721	-3.7%
15	739	740	-3.4%
16	748	754	-3.1%
17	757	764	-2.8%
18	766	775	-2.6%
19	774	784	-2.3%
20	781	793	-2.1%
21	789	802	-1.9%
22	796	803	-1.7%
23	802	807	-1.6%
24	809	814	-1.5%
25	815	821	-1.4%
26	820	829	-1.3%
27	826	843	-1.1%
28	832	855	-1.0%
29	837	880	-0.8%
30	842	874	-0.6%



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CS Standards Technical Service Co., Ltd.
Shunde Branch


1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

5.3 Furnace Pressure Record

The actual furnace pressure/time curves are shown in below figure.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300

t (86-757) 22805888

www.sgsgroup.com.cn

中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300


t (86-757) 22805888

sgs.china@sgs.com

5.4 Unexposed Surface Temperatures Record

The unexposed surface temperatures of the specimens were measured during the test.

Positions for measuring unexposed temperatures were shown below (unit: mm).



× - Positions of Thermocouples



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

The unexposed surface temperatures were shown on the table below:

Time (min)	Temperature (°C)										
	1#	2#	3#	4#	5#	6#	7#	8#	9#	Mean Rise	Max Rise
0	23	23	23	23	23	23	23	23	25	0	2
1	23	23	23	23	23	23	23	23	25	0	2
2	23	23	23	23	23	23	23	23	25	0	2
3	23	23	23	23	23	23	23	23	25	0	2
4	23	23	23	23	23	23	23	23	25	0	2
5	23	23	23	23	23	23	23	23	25	0	2
6	23	23	23	23	23	23	23	23	25	0	2
7	23	23	23	23	23	23	23	23	25	0	2
8	23	23	23	23	23	23	23	23	25	0	2
9	23	23	23	23	23	23	23	23	25	0	2
10	23	23	23	22	23	23	23	23	25	0	2
11	23	23	23	23	23	23	23	23	25	0	2
12	23	23	23	22	23	23	23	23	25	0	2
13	23	23	23	22	23	23	23	23	25	0	2
14	23	23	23	22	23	22	23	23	25	0	2
15	23	23	23	22	22	22	23	23	25	0	2
16	23	23	23	22	23	22	23	23	25	0	2
17	23	23	23	22	22	22	23	23	25	0	2
18	23	23	23	22	22	22	23	23	25	0	2
19	23	23	23	22	22	22	22	23	25	0	2
20	23	23	23	22	22	22	22	23	25	0	2
21	23	23	23	22	22	22	22	23	25	0	2
22	23	23	23	22	22	22	22	22	25	0	2
23	23	23	23	22	22	22	22	23	25	0	2
24	23	23	23	22	22	22	22	23	25	0	2
25	23	23	23	22	22	22	22	22	25	0	2
26	23	23	23	22	22	22	22	23	25	0	2
27	23	23	23	22	22	22	22	23	25	0	2
28	23	23	23	22	22	22	22	22	25	0	2
29	23	23	23	22	22	22	22	23	25	0	2
30	23	23	23	22	22	22	22	22	25	0	2


Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

The unexposed face temperature rise/time curves were shown in the figure below.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

5.5 Deflection Record

Time (min)	Deflection (mm)
0	0.0
1	0.0
2	1.3
3	1.7
4	2.6
5	2.4
6	2.4
7	2.6
8	2.7
9	2.9
10	3.0
11	3.1
12	3.4
13	3.3
14	3.8
15	4.1
16	4.1
17	4.1
18	4.1
19	4.1
20	4.3
21	4.8
22	4.7
23	5.3
24	5.3
25	5.7
26	6.2
27	6.7
28	6.4
29	6.1
30	7.2



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CS Standards Technical Service Co., Ltd.
Shunde Branch

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

5.6 Observations

Time		All observations were from the unexposed face unless noted otherwise
min	sec	
00	00	Furnace fired and test was started.
10	00	There were no visible significant changes to the unexposed face.
20	00	There were no visible significant changes to the unexposed face. The fiber-reinforced calcium silicate board on the unexposed face has local cracking.
28	00	There was smoke leakage on the unexposed face of the sample.
30	00	The sample was maintaining its integrity and insulation. The test was terminated.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

6. PERFORMANCE CRITERIA

The performance of the sample was assessed against the criteria for integrity and insulation in accordance with BS EN 1363-1:2020, Clause 11.

Integrity E:

These are the times in completed minutes for which the test specimen continues to maintain its separating function during the test without:

- a) causing the ignition of a cotton pad when applied, or
- b) permitting the penetration of a gap gauge as follows:
 - i. whether the 6 mm gap gauge can be passed through the test specimen, such that the gauge projects into the furnace, and can be moved a distance of 150 mm along the gap; or
 - ii. whether the 25 mm gap gauge can be passed through the test specimen such that the gauge projects into the furnace.
- c) resulting in sustained flaming for a period of time greater than 10 seconds.

Insulation I:

This is the time in completed minutes for which the test specimen continues to maintain its separating function during the test without developing temperatures on its unexposed surface which:

- a) increase the average temperature above the initial average temperature by more than 140 °C, or
- b) increase at any location (including the roving thermocouple) above the initial average temperature by more than 180 °C.

The performance criteria “insulation” shall automatically be assumed not to be satisfied when the “integrity” criterion ceases to be satisfied.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com



TEST REPORT

No.: SDFTS25007364R03_EN

Date: Dec 16, 2025

Page 14 of 19

7. CONCLUSION

The tested specimen has been subjected to a fire resistance test in accordance with EN 1364-2:2018, "Fire resistance tests for non-loadbearing elements – Part 2: Ceilings".

The fire resistance of the specimen was judged against the criteria for insulation and integrity as specified in the standard, and the specimen satisfied the performance requirements for the following period:

PERFORMANCE CRITERIA	RESULTS
Integrity	Sustained flaming 30 min
	Cotton pad test 30 min
	Gap gauge test 30 min
Insulation	30 min

The test was discontinued after a period of 30 minutes at the request of the sponsor.

8. CLASSIFICATION

8.1 Reference for Classification

This classification has been carried out in accordance with Clause 7.5.4 of EN 13501-2:2023.

8.2 Classification

Test and classification were performed from one side only. The element, FLOOR OF PREFABRICATED HOUSES, was classified to be:

EI 30 (a←b)

Where, "a" referring to above and "b" to below the membrane, and EI 30 (a←b) indicates the specimen was capable of providing 30 min integrity and thermal insulation performance from the upside only.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300

t (86-757) 22805888

www.sgsgroup.com.cn

中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888

sgs.china@sgs.com

9. LIMITATION

The results only relate to the behaviour of the sample of the element of construction under the particular conditions of the test. They are not intended to be the sole criteria for assessing the potential fire performance of the element in use nor do they reflect the actual behaviour in fires.

The sample was asymmetrical and was tested on the specified surface towards the heating conditions of the test. The test result may not be appropriate to the situation on the other side towards the heating conditions.

This report details the method of construction, the test conditions and the results obtained when the specific element of construction described herein was tested following the procedure outlined in EN 1363-1, and where appropriate EN 1363-2. Any significant deviation with respect to size, constructional details, loads, stresses, edge or end conditions other than those allowed under the field of direct application in the relevant test method is not covered by this report.

Because of the nature of fire resistance testing and the consequent difficulty in quantifying the uncertainty of measurement of fire resistance, it is not possible to provide a stated degree of accuracy of the result.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com

APPENDIX 2 - PHOTOS



The unexposed side before the test



The exposed side before the test



SGS-CS Standards Technical Service Co., Ltd.
Shunde Branch

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com



The unexposed side after 20 minutes of testing



The unexposed side after 29 minutes of testing




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com



The unexposed side after 30 minutes of testing



The exposed side after the test

SGS authenticate the photo on original report only

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgsgroup.com.cn
t (86-757) 22805888 sgs.china@sgs.com